# Tile Adhesives



#### PRODUCT DESCRIPTION

weber.tai 2-in-1 is an innovative tile adhesive with water prevention property to mix with water using to lay tiles in bathrooms, kitchens, and any areas in contact with water

• SUITABLE FOR: ceramic tiles, granito tiles, marbles, granites, artificial tiles size υρ to 1 x 1 m.

• PACKAGING: 5 kg bag and 20 kg bag

• COLOR: grey

• COVERAGE: average 1 m²/5 kg bag

average 4 m²/20 kg bag

#### APPLICATION

### Substrate preparation

- New substrate should be sound, level, and clean with normal absorption rate  $% \left( 1\right) =\left( 1\right) \left( 1\right) +\left( 1\right) \left( 1\right) \left( 1\right) +\left( 1\right) \left( 1\right) \left$
- Case of existing substrate; check bonding. Remove peel-off paint and de-bonded tiles and lay the new ones. Clean off any excess dirt and laitance.
- In case of porous substrate with high absorption, dampen the surface before tiling
- For new render or screed, it should be fully cured at the rate of 7 days per 1 cm thickness before tiling

## Mixing

Mixing weber.tai 2-in-1 in water with the ratio of 1:3 by volume (1 part of water + 3 parts of weber.tai 2-in-1). Using slow-speed electric mixer to mix or gradually mix by hand until obtaining homogeneous lump-free paste. Leave for 3 – 4 minutes for chemical curing before using.

#### Tiling

- 1. Using notched trowel to spread tile adhesive onto substrate
- 2. Back buttering in case of laying tile bigger than 10 x 10 inches
- 3. Placing tiles on tile adhesive and knock gradually with rubber hammer
- 4. Clean the excess tile adhesive on tile surface
- 5. Tiles can be adjusted within 15 minutes after laying
- 6. Leave for 24 hours before grouting

#### SHELF LIFE AND STORAGE

One year after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag

#### **TECHNICAL DATA**

Туре	High performance tile adhesive
Density of powder	1.35 g/cm³
Chemical curing time	3 – 4 minutes
Pot life (in shade)	4 hours
Open time	20-30 minutes
Adjusting time	15 minutes
Recommended thickness	2 – 10 mm
Waiting time before grouting	24 hours

**Remark:** These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

# CERTIFIED STANDARD

International/European standard	Standard	Result
Initial tensile adhesion strength ISO 13007 part 2-4.4.4.2 or EN 1348-8.2	≥1.0 N/mm²	1.70 N/mm²
Tensile adhesion strength after water immersion ISO 13007 part 2-4.4.4.3 or EN 1348-8.3	≥1.0 N/mm²	1.10 N/mm²
American Standard	Standard	Result
Shear strength to glazed wall tiles at 28 days according to ANSI 118.4 – 1999: F – 5.1.5	≥20.9 kg/cm²	22.1 kg/cm²
28 days	≥20.9 kg/cm² ≥14.0 kg/cm²	22.1 kg/cm <sup>2</sup> 35.8 kg/cm <sup>2</sup>

