

High quality tile adhesive with double bonding strength



Laying ceramic tiles, grando tiles, granites up to size 60 x 60 cm on both floor and wall



With special additive providing anti-slip property



Double bonding strength



Low VOCs

### PRODUCT DESCRIPTION

weber.tai fix is pre-mixed high quality tile adhesive to mix with water giving double bonding strength for laying tiles on both floors and walls

**SUITABLE FOR:** ceramic tiles, clay tiles, grando tiles, marbles, granites size up to 60 x 60 cm

**PACKAGING:** 20 kg bag and 25 kg bag

**COLOR:** grey

**COVERAGE:** average 4 m<sup>2</sup>/20 kg bag  
average 5 m<sup>2</sup>/25 kg bag

### APPLICATION

#### Substrate preparation

- Substrate should be sound, level, and clean with normal absorption rate
- In case of porous substrate with high absorption, dampen the surface before tiling
- For new render or screed, it should be fully cured at the rate of 7 days per 1 cm thickness before tiling

#### Mixing

Mixing weber.tai fix in water with the ratio of 1:3 by volume (1 part of water + 3 parts of weber.tai fix). Using slow-speed electric mixer to mix or gradually mix by hand until obtaining homogeneous lump-free paste. Leave for 3 – 4 minutes for chemical curing before using.

#### Tiling

1. Using notched trowel to spread tile adhesive onto substrate
2. Back buttering in case of laying tile bigger than 10 x 10 inches
3. Placing tiles on tile adhesive and knock gradually with rubber hammer
4. Clean the excess tile adhesive on tile surface
5. Tiles can be adjusted within 15 minutes after laying
6. Leave for 24 hours before grouting

### SHELF LIFE AND STORAGE

One year after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag

### TECHNICAL DATA

Type	Standard tile adhesive
Density of powder	14 g/cm <sup>3</sup>
Chemical curing time	3 – 4 minutes
Pot life (in shade)	4 hours
Open time	20-30 minutes
Adjusting time	15 minutes
Recommended thickness	2 – 10 mm
Waiting time before grouting	24 hours

Remark: These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

### CERTIFIED STANDARD

International/European standard	Standard	Result
Initial tensile adhesion strength ISO 13007 part 2-4.4.4.2 or EN 1348-8.2	≥0.5 N/mm <sup>2</sup>	1.46 N/mm <sup>2</sup>
Tensile adhesion strength after water immersion ISO 13007 part 2-4.4.4.3 or EN 1348-8.3	≥0.5 N/mm <sup>2</sup>	1.31 N/mm <sup>2</sup>
Open time tensile adhesion strength ISO 13007 part 2-4.1 or EN 1346	≥0.5 N/mm <sup>2</sup>	0.72 N/mm <sup>2</sup>
American Standard	Standard	Result
Shear strength according to ANSI 118.1 – 2012		
- To glazed wall tiles 7 days	≥14.06 ksc	19.9 ksc
- To porcelain mosaics 1 day	≥3.52 ksc	8.1 ksc
7 days	≥10.55 ksc	12.6 ksc
28 days	≥10.55 ksc	18.1 ksc
84 days	≥10.55 ksc	16.7 ksc
Water immersion shear strength according to ANSI 118.2 – 2012		
- To glaze wall tiles 7 days	≥10.55 ksc	16.4 ksc
- To porcelain mosaic 7 days	≥7.03 ksc	12.9 ksc

